



Pigment Specialist

上海秀乐化工科技有限公司
Shanghai Supercolor Chemical Technology Co., Ltd

Address: Bldg. 2, No. 1500 Xinfei Rd., Songjiang Industrial Zone, Shanghai, China 201611
Tel: 86-21-67601407, 67601408 Fax: 86-21-51026050, 67600928
E-mail: cnabrightzh@hotmail.com brightzh@supercolor.cn

Pigment Name	Color Index No.	Fastness Property		
		Heat Resistance (C)	Light Fastness	Migration
Suplasto Yellow SC-GR02	C.I.Pigment Yellow 13	200	6~7	4~5
Suplasto Yellow SC-WSR	C.I.Pigment Yellow 62	230	7~8	4~5
Suplasto Yellow SC-HR02	C.I.Pigment Yellow 83	200	7~8	4
Suplasto Yellow SC-3RN	C.I.Pigment Yellow 110	260	7~8	5
Suplasto Yellow SC-H961	C.I.Pigment Yellow 138	250	7~8	4~5
Suplasto Yellow SC-H2R	C.I.Pigment Yellow 139	210	7	5
Suplasto Yellow SC-WGP	C.I.Pigment Yellow 168	230	6~7	4~5
Suplasto Yellow SC-HG	C.I.Pigment Yellow 180	280	7~8	4~5
Suplasto Yellow SC-KP	C.I.Pigment Yellow 183	270	7~8	4~5
Supigmento Orange SC-GP	C.I.Pigment Orange 64	280	7~8	5
Suplasto Red SC-2BP	C.I.Pigment Red 48:2	240	6~7	4~5
Suplasto Red SC-2BSP	C.I.Pigment Red 48:3	220	6~7	4~5
Suplasto Red SC-4BP	C.I.Pigment Red 57:1	240	6~7	4~5
Suplasto Red SC-ED	C.I.Pigment Red 122	280	7~8	5
Suplasto Red SC-BRN	C.I.Pigment Red 144	280	7~8	5
Suplasto Red SC-RN	C.I.Pigment Red 166	280	7~8	5
Suplasto Red SC-F5RK	C.I.Pigment Red 170	240	6~7	4~5
Suplasto Red SC-F3RK	C.I.Pigment Red 170	260	6~7	4~5
Suplasto Red SC-30	C.I.Pigment Red 254	300	7~8	5
Suplasto Violet SC-RLP	C.I.Pigment Violet 23	260	7~8	5
Suplasto Blue SC-BS512	C.I.Pigment Blue 15:1	300	7~8	5
Suplasto Blue SC-BGSP	C.I.Pigment Blue 15:3	300	7~8	5
Suplasto Green SC-GP	C.I.Pigment Green 7	280	7~8	5